

Application No.: 10/657,730

Amendment Dated March 7, 2007

Reply to Office Action of September 7, 2006

Amendments to the Claims:

1. (currently amended) A method for beneficiating slag from coal gasification, comprising:
 - mixing the slag from coal gasification with water to form a slurry;
 - screening the slurry through a substantially planar first screen to remove a first portion of material, wherein the first portion of material has a particle size exceeding approximately .5 inches;
 - screening the slurry subsequent to said first screening step through a substantially planar second screen to remove a second portion of material, wherein the second portion of material has a particle size of between approximately .5 inches and approximately 840 μ m; and
 - wherein the second portion of material has a carbon content less than about 5%.
2. (original) A method according to Claim 1 wherein the second portion of material has a carbon content less than about 1%.
3. (canceled)
4. (canceled)
5. (original) A method according to Claim 1 further comprising dewatering a slurry prior to said mixing step.
6. (original) A method according to Claim 1 wherein said mixing step comprises agitating the slurry.
7. (original) A method according to Claim 1 further comprising spraying a fluid onto at least one of the first and second screens concurrently with said corresponding first and second screening steps.

Application No.: 10/657,730
Amendment Dated March 7, 2007
Reply to Office Action of September 7, 2006

8. (original) A method according to Claim 1 further comprising vibrating at least one of the first and second screens concurrently with said corresponding first and second screening steps.

9. (original) A method according to Claim 1 further comprising screening the slurry subsequent to said second screening step through a centrifuge to remove a third portion of material.

10. (original) A method according to Claim 9 wherein the third portion of material has a particle size of between approximately 840 μm and approximately 45 μm .

11. (previously presented) A method according to Claim 9 further comprising using the third portion of material as at least one of a carbon-based combustible fuel and an adsorbent carbon.

12. (original) A method according to Claim 9 further comprising thickening the slurry subsequent to said third screening step using an anionic flocculant selected from the group consisting of polyacrylamide and acrylamide copolymers to thereby remove a fourth portion of material from the slurry.

13. (original) A method according to Claim 12 further comprising using a pH modifier selected from the group consisting of sodium hydroxide and ammonium hydroxide to clarify the water.

14. (original) A method according to Claim 12 wherein the fourth portion of material has a particle size of less than approximately 45 μm .

15. (original) A method according to Claim 12 further comprising processing the fourth portion of material using a belt filtering press.

Application No.: 10/657,730
Amendment Dated March 7, 2007
Reply to Office Action of September 7, 2006

16. (previously presented) A method according to Claim 15 further comprising using the processed fourth portion of material as a carbon-based combustible fuel.

17. (withdrawn) A method according to Claim 1 further comprising screening the slurry subsequent to said second screening step using a hydrocyclone to remove a third portion of material from the slurry.

18. (withdrawn) A method according to Claim 17 wherein the third portion of material has a particle size of between approximately 840 μm to approximately 75 μm .

19. (withdrawn) A method according to Claim 17 further comprising dewatering the third portion of material subsequent to said third screening step using a centrifuge.

20. (withdrawn) A method according to Claim 17 further comprising using the third portion of material as at least one of an adsorbent carbon and fuel product.

21. (withdrawn) A method according to Claim 17 further comprising thickening the slurry subsequent to said third screening step using an anionic flocculant selected from the group consisting of polyacrylamide and acrylamide copolymers to thereby remove a fourth portion of material from the slurry.

22. (withdrawn) A method according to Claim 21 wherein the fourth portion of material has a particle size of less than approximately 75 μm .

23. (withdrawn) A method according to Claim 21 further comprising using a pH modifier selected from the group consisting of sodium hydroxide and ammonium hydroxide to clarify the water.

Application No.: 10/657,730
Amendment Dated March 7, 2007
Reply to Office Action of September 7, 2006

24. (withdrawn) A method according to Claim 21 further comprising processing the fourth portion of material using a belt filtering press.

25. (withdrawn) A method according to Claim 24 further comprising using the processed fourth portion of material as a fuel product.

26. (currently amended) A method for beneficiating slag from coal gasification, comprising:

mixing the slag from coal gasification with water to form a slurry;

screening the slurry through a substantially planar first screen to remove a first portion of material, wherein the first portion of material has a particle size exceeding approximately .5 inches;

screening the slurry subsequent to said first screening step through a substantially planar second screen to remove a second portion of material, wherein the second portion of material has a particle size of between approximately .5 inches and approximately 840 μ m;

screening the slurry subsequent to said second screening step through a centrifuge to remove a third portion of material, wherein the third portion of material has a particle size of between approximately 840 μ m and approximately 45 μ m; and

wherein the second portion of material has a lower carbon content than the third portion of material.

27. (original) A method according to Claim 26, wherein the second portion of material has a carbon content less than about 5%.

28. (canceled)

29. (canceled)

Application No.: 10/657,730
Amendment Dated March 7, 2007
Reply to Office Action of September 7, 2006

30. (original) A method according to Claim 26 further comprising dewatering a slurry prior to said mixing step.

31. (original) A method according to Claim 26 wherein said mixing step comprises agitating the slurry.

32. (original) A method according to Claim 26 further comprising spraying a fluid onto at least one of the first and second screens concurrently with said corresponding first and second screening steps.

33. (original) A method according to Claim 26 further comprising vibrating at least one of the first and second screens concurrently with said corresponding first and second screening steps.

34. (canceled)

35. (previously presented) A method according to Claim 26 further comprising using the third portion of material as at least one of a carbon-based combustible fuel and an adsorbent carbon.

36. (original) A method according to Claim 26 further comprising thickening the slurry subsequent to said third screening step using an anionic flocculant selected from the group consisting of polyacrylamide and acrylamide copolymers to thereby remove a fourth portion of material from the slurry.

37. (original) A method according to Claim 36 further comprising using a pH modifier selected from the group consisting of sodium hydroxide and sodium hydroxide to clarify the water.

Application No.: 10/657,730
Amendment Dated March 7, 2007
Reply to Office Action of September 7, 2006

38. (original) A method according to Claim 36 wherein the fourth portion of material has a particle size less than approximately 45 μm .

39. (original) A method according to Claim 36 further comprising processing the fourth portion of material using a belt filtering press.

40. (previously presented) A method according to Claim 39 further comprising using the processed fourth portion of material as at least one of a carbon-based combustible fuel and a adsorbent carbon.

41. (withdrawn) A method for beneficiating slag, comprising:
mixing the slag with water to form a slurry;
screening the slurry through a first screen to remove a first portion of material;
screening the slurry subsequent to said first screening step through a second screen to remove a second portion of material;
screening the slurry subsequent to said second screening step using a hydrocyclone to remove a third portion of material from the slurry; and
wherein the second portion of material has a lower carbon content than the third portion of material.

42. (withdrawn) A method according to Claim 41, wherein the second portion of material has a carbon content less than about 5%.

43. (withdrawn) A method according to Claim 41 wherein the first portion of material has a particle size exceeding approximately .5 inches.

44. (withdrawn) A method according to Claim 41 wherein the second portion of material has a particle size of between approximately .5 inches and approximately 840 μm .

Application No.: 10/657,730
Amendment Dated March 7, 2007
Reply to Office Action of September 7, 2006

45. (withdrawn) A method according to Claim 41 further comprising dewatering a slurry prior to said mixing step.

46. (withdrawn) A method according to Claim 41 wherein said mixing step comprises agitating the slurry.

47. (withdrawn) A method according to Claim 41 further comprising spraying a fluid onto at least one of the first and second screens concurrently with said corresponding first and second screening steps.

48. (withdrawn) A method according to Claim 41 further comprising vibrating at least one of the first and second screens concurrently with said corresponding first and second screening steps.

49. (withdrawn) A method according to Claim 41 wherein the third portion of material has a particle size of between approximately 840 μm to approximately 75 μm .

50. (withdrawn) A method according to Claim 41 further comprising dewatering the third portion of material subsequent to said third screening step using a centrifuge.

51. (withdrawn) A method according to Claim 41 further comprising using the third portion of material as at least one of an adsorbent carbon and a fuel product.

52. (withdrawn) A method according to Claim 41 further comprising thickening the slurry subsequent to said fourth screening step using an anionic flocculant selected from the group consisting of polyacrylamide and acrylamide copolymers to thereby remove a fourth portion of material from the slurry.

Application No.: 10/657,730
Amendment Dated March 7, 2007
Reply to Office Action of September 7, 2006

53. (withdrawn) A method according to Claim 52 wherein the fourth portion of material has a particle size of less than approximately 75 μm .

54. (withdrawn) A method according to Claim 52 further comprising using a pH modifier selected from the group consisting of sodium hydroxide and ammonium hydroxide to clarify the water.

55. (withdrawn) A method according to Claim 52 further comprising processing the fourth portion of material using a belt filtering press.

56. (withdrawn) A method according to Claim 55 further comprising using the processed fourth portion of material as at least one of a fuel product or adsorbent carbon.

57. (currently amended) A system for beneficiating a slag slurry comprising slag from coal gasification into usable portions, comprising:

a substantially planar first screen for removing a first portion of material from the slurry, wherein the slurry comprises slag from coal gasification and wherein the first portion of material has a particle size exceeding approximately .5 inches;

a substantially planar second screen for removing a second portion of material from the slurry, wherein the second portion of material has a particle size of between approximately .5 inches and approximately 840 μm ; and

wherein the second portion of material has a carbon content of less than about 5%.

58. (original) A system according to Claim 57 wherein the second portion of material has a carbon content less than about 1%.

59. (canceled)

60. (canceled)

Application No.: 10/657,730
Amendment Dated March 7, 2007
Reply to Office Action of September 7, 2006

61. (original) A system according to Claim 57 further comprising a blunger for agitating the slurry.

62. (original) A system according to Claim 57 further comprising at least one sprayer for spraying fluid onto at least one of the first and second screens.

63. (original) A system according to Claim 57 further comprising at least one vibrator for vibrating at least one of said first and second screens.

64. (original) A system according to Claim 57 further comprising a centrifuge for removing a third portion of material from the slurry.

65. (original) A system according to Claim 64 wherein the third portion of material has a particle size of between approximately 840 μm to approximately 45 μm .

66. (original) A system according to Claim 57 further comprising a thickener for removing a fourth portion of material from the slurry.

67. (original) A system according to Claim 66 further comprising a belt filtering press for dewatering the fourth portion of material.

68. (withdrawn) A system according to Claim 57 further comprising a hydrocyclone for removing a third portion of material from the slurry.

69. (withdrawn) A system according to Claim 68 wherein the third portion of material has a particle size of between approximately 840 μm to approximately 75 μm .

Application No.: 10/657,730
Amendment Dated March 7, 2007
Reply to Office Action of September 7, 2006

70. (withdrawn) A system according to Claim 68 further comprising a centrifuge for dewatering the third portion of material.

71. (withdrawn) A system according to Claim 68 further comprising a thickener for removing a fourth portion of material from the slurry.

72. (withdrawn) A system according to Claim 71 further comprising a belt filtering press for dewatering the fourth portion of material.

73. (currently amended) A system for beneficiating a slag slurry comprising slag from coal gasification into usable portions, comprising:

a substantially planar first screen for removing a first portion of material from the slurry, wherein the slurry comprises slag from coal gasification and wherein the first portion of material has a particle size exceeding approximately .5 inches;

a substantially planar second screen for removing a second portion of material from the slurry, wherein the second portion of material has a particle size of between approximately .5 inches and approximately 840 μm ;

a centrifuge for removing a third portion of material from the slurry; and wherein the second portion of material has a lower carbon content than the third portion of material.

74. (original) A system according to Claim 73 wherein the second portion of material has a carbon content less than about 5%.

75. (canceled)

76. (canceled)

Application No.: 10/657,730
Amendment Dated March 7, 2007
Reply to Office Action of September 7, 2006

77. (original) A system according to Claim 73 further comprising a blunger for agitating the slurry.

78. (original) A system according to Claim 73 further comprising at least one sprayer for spraying fluid onto at least one of the first and second screens.

79. (original) A system according to Claim 73 further comprising at least one vibrator for vibrating at least one of said first and second screens.

80. (original) A system according to Claim 73 wherein the third portion of material has a particle size of between approximately 840 μm and approximately 45 μm .

81. (original) A system according to Claim 73 further comprising a thickener for removing a fourth portion of material from the slurry.

82. (original) A system according to Claim 81 further comprising a belt filtering press for dewatering the fourth portion of material.

83. (withdrawn) A system for beneficiating a slag slurry into usable portions, comprising:

- a first screen for removing a first portion of material from the slurry;
- a second screen for removing a second portion of material from the slurry;
- a hydrocyclone for removing a third portion of material from the slurry; and

wherein the second portion of material has a lower carbon content than the third portion of material.

84. (withdrawn) A system according to Claim 83 wherein the second portion of material has a carbon content less than about 5%.

Application No.: 10/657,730
Amendment Dated March 7, 2007
Reply to Office Action of September 7, 2006

85. (withdrawn) A system according to Claim 83 wherein the first portion of material has a particle size exceeding approximately .5 inches.

86. (withdrawn) A system according to Claim 83 wherein the second portion of material has a particle size of between approximately .5 inches and approximately 840 μm .

87. (withdrawn) A system according to Claim 83 further comprising a blunger for agitating the slurry.

88. (withdrawn) A system according to Claim 83 further comprising at least one sprayer for spraying fluid onto at least one of the first and second screens.

89. (withdrawn) A system according to Claim 83 further comprising at least one vibrator for vibrating at least one of said first and second screens.

90. (withdrawn) A system according to Claim 83 wherein the third portion of material has a particle size between approximately 840 μm to approximately 75 μm .

91. (withdrawn) A system according to Claim 83 further comprising a centrifuge for dewatering the third portion of material.

92. (withdrawn) A system according to Claim 83 further comprising a thickener for removing a fourth portion of material from the slurry.

93. (withdrawn) A system according to Claim 92 further comprising a belt filtering press for dewatering the fourth portion of material.